

Abstrakt

Ziel: Die Non Invasive Keratograph Dry Up Time ([NIK-DUT](#))-Messung wird bei weichen Kontaktlinsen bereits für Materialvergleiche *in vitro* und *in vivo* angewandt. Hauptziel dieser Pilotstudie ist die erstmalige Anwendung dieser Technologie bei einem Materialvergleich zweier formstabiler Kontaktlinsenmaterialien (Roflufococon C und Enflufococon B) in Hinsicht auf die Benetzbarkeit mittels der [NIK-DUT](#)-Messung. Ein weiteres Hauptziel ist der subjektive Materialvergleich mittels Fragebogen.

Methode: Die Studie ist im Rahmen einer explorativen Anwendungsbeobachtung angelegt. Sie ist longitudinal und umfasst drei Untersuchungstermine: Baselineuntersuchung, Abgabe der Studienkontakteinsen und Nachkontrolle der Studienkontakteinsen. Die Proband:innen tragen die zwei Materialien im R/L-Vergleich. Bei der Abgabe der Studienkontakteinsen und nach einer Testphase von mindestens 6 Tagen wird die durchschnittliche [NIK-DUT](#) gemessen und Fragebögen über den Tragekomfort ausgefüllt. Daraufhin wird das individuell bessere Material für den/die Proband:in bestimmt.

Ergebnisse: Die [NIK-DUT](#)-Messung wurde qualitativ ausgewertet. Es wurde kein Unterschied in der Benetzbarkeit zwischen den Materialien gefunden. Die Ergebnisse der Fragebögen ergaben einen schlechteren Tragekomfort bei Roflufococon C im Vergleich zu Enflufococon B um 1,5 Stufen im Klassifizierungsschlüssel am Ende der Tragezeit. Enflufococon B wird im Median von Beginn zu Ende der Tragezeit gleich mit „1“/„gut“ bewertet. Roflufococon C hingegen wird zu Beginn besser als Enflufococon B mit „0,5“/„exzellent bis gut“ bewertet, jedoch verschlechtert sich die Bewertung im Laufe der Tragezeit um 2 Stufen auf „2,5“/„befriedigend bis ausreichend“. Es entschieden sich alle Proband:innen (n=4) mit trockenen Augen für Enflufococon B. 3 von 4 Proband:innen mit lipidreichen Tränenfilmen entschieden sich für Enflufococon B.

Schlussfolgerung: Die [NIK-DUT](#)-Messung ist momentan für die quantitative Beurteilung der Benetzbarkeit von formstabilen Kontaktlinsen nicht geeignet. Im subjektiven Materialvergleich scheint Enflufococon B besser geeignet zu sein für Kontaktlinsenträger:innen mit trockenen und/oder lipidreichen Tränenfilmen. Der schlechtere Tragekomfort am Ende der Tragezeit bei Roflufococon C könnte durch Flexen verursacht werden. Diese Hypothesen sind jedoch in nachfolgenden Studien zu evaluieren.

Schlüsselwörter: formstabile/[RGP](#) Kontaktlinsen, Materialvergleich, [NIK-DUT](#), Benetzbarkeit, Tragekomfort

Abstract

Purpose: Using the measurement of Non Invasive Keratograph Dry Up Time (**NIK-DUT**) for the comparison of soft contact lens materials is already established for in vivo and in vitro studies. The main aim of this pilot study is to adapt the method to **RGP** contact lens materials. Therefore, Roflufococon C and Enflufococon B are tested with respect to the wettability. Another main objective is the subjective comparison of materials by means of a questionnaire.

Method: The study is designed as an exploratory observational study. It is a longitudinal study and includes three examination dates: Baseline examination, study contact lens dispensing and study contact lens follow-up. The participants wear both contact lens materials at the same time in right/left comparison. During the second and third appointment the average **NIK-DUT** is measured and the comfort in terms of wearing the contact lenses is asked by a questionnaire. The test-phase of the contact lenses was at least 6 days. At the third appointment the best material for each participant is determined.

Results: The results of the **NIK-DUT** measurement are evaluated in a qualitative way. No difference in wettability was found between both materials. The results of the questionnaires showed that Roflufococon C was less comfortable to wear compared to Enflufococon B by 1.5 levels in the classification key at the end of the wearing period. Enflufococon B was given the same median rating of „1“/„good“ from the beginning to the end of the wearing period. Roflufococon C, on the other hand, is rated better than Enflufococon B at the beginning with „0.5“/„excellent to good“, but the rating deteriorates in the course of the wearing period by 2 levels to „2.5“/„satisfactory to sufficient“. All participants with dry eyes (n=4) decided to wear Enflufococon B. 3 out of 4 test persons with lipid-rich tear films opted for Enflufococon B.

Conclusion: Under the current conditions, the **NIK-DUT** is not the adequate measurement to evaluate the wettability of **RGP** contact lenses quantitatively. In the subjective comparison of materials, Enflufococon B appears to be more suitable for contact lens wearers with dry eye and for contact lens wearers with lipid-rich tear films. A possible reason for the decrease of comfort wearing Roflufococon C could be flexing of the contact lenses. However, these hypotheses must be evaluated in subsequent studies.

Keywords: **RGP** contact lenses, comparison of contact lens materials, **NIK-DUT**, wettability, comfort in terms of wearing contact lenses